Dielectric anomalies above the glass transition in the mixed $K_{1-x}(NH_4)_xH_2PO_4$ crystals

Authors: A.I. Baranov, L.A. Shuvalov, and V.H. Schmidt

This is an Accepted Manuscript of an article published in [Ferroelectrics](#) on February 10, 2011, available online: <http://www.tandfonline.com/10.1080/00150199208223379>.

A.I. Baranov, L.A. Shuvalov, and V.H. Schmidt, "Dielectric anomalies above the glass transition in the mixed $K_{1-x}(NH_4)_xH_2PO_4$ crystals," *Ferroelectrics* 127, 245-250 (1992).
<http://dx.doi.org/10.1080/00150199208223379>

Made available through Montana State University's [ScholarWorks](#)
scholarworks.montana.edu

DIELECTRIC ANOMALIES ABOVE THE GLASS TRANSITION IN THE MIXED $K_{1-x}(NH_4)_xH_2PO_4$ CRYSTALS

A.I. Baranov, L.A. Shuvalov
Inst. of Crystallography Acad. Sci. USSR, Moscow

and V.H. Schmidt
Dep. of Physics, Montana St. University, Bozeman,
MT, USA

Abstract The temperature dependences of the complex dielectric constant have been measured in the mixed $K_{1-x}(NH_4)_xH_2PO_4$ crystals at frequencies 10Hz-100kHz. For ammonium concentrations $0.3 \leq x \leq 0.6$ pronounced dielectric anomalies in c-direction has been detected in the temperature range 200-260K. It was found that in this temperature range the dielectric relaxation dispersion is changed dramatically.

INTRODUCTION

In the last years experimental studies of the mixed $K_{1-x}(NH_4)_xH_2PO_4$ (KADP) crystals have been done¹⁻⁵ to found the glass properties similar to those observed in $Rb_{1-x}(NH_4)_xH_2PO_4$ (RADP) and other mixed crystals⁶⁻⁸. The results of these investigations point out that mixed KADP crystals exhibit a proton glass behavior for $0.23 \leq x \leq 0.6$ ^{3,5}. The analysis of the dielectric data given in the literature usually refers to the low-temperature region ($T < 200K$). However the recent dielectric measurements of the KADP ($x=0.6$) showed the pronounced anomalies of the temperature dependences of the complex dielectric constant $\epsilon'_c + i\epsilon''_c$ near 240K except the low-temperature anomalies at the glass transition $T_g=23K$ ^{6,7}.

In the present paper in order to clarify the general features of the high-temperature anomalies in the mixed KADP crystals we measured the temperature dependences of $\epsilon'_c + i\epsilon''_c$ for the compositions with $x=0.3, 0.5, 0.6$ and 1.0 in the temperature range 100-400K.

THE EXPERIMENTAL

The KADP single crystals investigated in this study were grown by slow cooling of the aqueous solutions with ammonium concentrations $X=0,5, 0,6, 0,65$ and $1,0$. The ammonium concentrations in crystals x determined from the relationship between X and x [3] and x is $0,3, 0,5, 0,6$ and $1,0$ respectively.

The experiments were performed on the plates $0,7 \times 0,7 \times 0,08 \text{ cm}^3$ of the c-cut. The conducting silver paint was used as electrodes. The sample was inserted into vacuum (dry air) cryostat and temperature was controlled by copper-constantan thermocouple. The complex dielectric constant $\epsilon'_c + i\epsilon''_c$ have been measured by Ando Electric TR - 10C and General Electric 1616 bridges in frequency range $10\text{Hz} - 100\text{kHz}$.

RESULTS AND DISCUSSION

The temperature dependencies of ϵ'_c are shown in Fig.1,2, for the different ammonium concentrations and some characteristic frequencies. For high frequencies ($\nu \geq 10\text{kHz}$) the pure ADP shows the apparent Curie - Weiss behavior from the phase transition temperature up to 370K . The Curie constant C is $7 \cdot 10^3 \text{K}$. The frequency dispersion which occurs at $T \approx 310\text{K}$, leads to the deviation of the low-frequency dielectric constant from a Curie-Weiss law (Fig.1). The $\epsilon'_c(T)$ dependences of the mixed KADP crystals have the same general behavior and obey the Curie-Weiss law only below 220K . The values of C are $(4.8 + 5.2) \cdot 10^3 \text{K}$ for different compositions. The strong dielectric dispersion occurs just above 220K . Furthermore, on cooling the inverse dielectric constant $1/\epsilon'_c$ shows the broad minimum near $T_m = 240\text{K}$ for KADP ($x=0,5, x=0,6$) and near $T_m = 250\text{K}$ for KADP ($x=0,3$) (Fig.1,2). On heating the observed dielectric anomalies are more pronounced than on cooling and are shifted to the high

FIGURE 1 The temperature dependences of the inverse dielectric constant for mixed KADP crystals. The open symbols correspond to the frequency 10kHz, the closed symbols correspond to the frequency 30Hz.

FIGURE 2 The temperature dependences of the inverse dielectric constant for KADP ($x=0,3$) at the frequency 30Hz.

temperatures (Fig.2). The amplitude of these anomalies decreases with increasing the frequency.

For sufficiently high temperatures the dielectric data can be analysed in the terms of Cole-Cole plots (Fig.3,4). In these figures the dielectric loss ϵ_c'' was determined as

$$\epsilon_c''(\nu, T) = \frac{\sigma(\nu, T) - \sigma_{dc}(T)}{2\pi\nu} \quad (1)$$

where σ_{dc} is dc conductivity. At $T \gtrsim 250\text{K}$ the mixed crystals show two well separated relaxation modes. The low-frequency mode is related to dc conductivity⁴. Figure 3 demonstrates the decreasing of the relaxation intensity of this mode when dc conductivity as grown KADP ($x=0,6$) decreased about 30 % after annealing. It should be noted that in our frequency window the low-frequency dispersion process disappears at $T > T_m$.

The high frequency relaxation mode is observed for the mixed crystals only. At $T > T_m$ this mode is characterised by a broad distribution of the relaxation times and can be described by the Cole-Cole equation

$$\epsilon_c' + i\epsilon_c'' = \epsilon_\infty + \frac{\epsilon_c^0 - \epsilon_\infty}{(1 + i2\pi\nu\tau)^{1-\alpha}} \quad (2)$$

where α does not depend practically on temperature (Fig. 3) up to $T \simeq T_m$.

In the vicinity of T_m the relaxation dispersion is changed dramatically and below T_m can be described by the equation

$$\epsilon_c' + i\epsilon_c'' = \epsilon_\infty + \epsilon''(i\omega\tau)^\gamma \quad (3)$$

where $\gamma \approx 0,6$. The high frequency relaxation is sensitive to the sample history. Figure 4 shows irreversible decreasing of the relaxation intensity after heating and cooling of the "virgin" sample. This fact suggests a close analogy of KADP with real glasses.

Summarizing these results we can tentatively relate the anomalous dielectric behavior of the mixed KADP

FIGURE 3 Cole-Cole representation of the complex dielectric constant for KADP ($x=0,6$) at different temperatures.

FIGURE 4 Cole-Cole representation of the complex dielectric constant for KADP ($x=0,6$) at room temperature 1-the "virgin" sample; 2-after the heating of the "virgin" sample; 3-after three cooling cycles.

crystals with rearrangement and orientational freezing of NH_4 groups at $T \leq T_m$.

ACKNOWLEDGEMENTS

We are grateful to Dr. R.M.Phedosuk for providing the samples.

REFERENCES

- 1.B.K.Choi, K.S.Lee, I.I.Kim, Jap. Journ. Appl. Phys., 24, 972, (1985).
- 2.K.S.Lee, K.T.Kim, J.J.Kim, Jap. Journ. Appl. Phys., 24, 969, (1985).
- 3.Y.Ono, T.Hikita, T.Ikeda, Ferroelectrics, 79, 327, (1988)
- 4.A.I.Baranov, V.H.Schmidt, L.A.Shuvalov, Ferroelectrics, (1991), to be published.
- 5.A.I.Baranov, V.H.Schmidt, S.Vaplijak, to be published.
- 6.E.Courtens, Phys. Rev. Lett., 52, 69 (1984).
- 7.Z.Tribula, V.H.Schmidt, J.E.Drumheller, Di He, Z.Li, Phys. Rev. B, 40, 5289, (1989).
- 8.V.T.Hochli, K.Knorr, A.Loidl, Adv.Physics 39, 405, ' (1990).